

2913

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 291 395 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
12.03.2003 Bulletin 2003/11

(51) Int Cl.7: **C09D 5/26**(21) Application number: **02255948.8**(22) Date of filing: **27.08.2002**

(84) Designated Contracting States:  
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR  
IE IT LI LU MC NL PT SE SK TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **07.09.2001 GB 0121640**

(71) Applicant: **ROLLS ROYCE PLC**  
**London SW1E 6AT (GB)**

(72) Inventors:

- **Watson, Hugh Michael Lawrence**  
**Derby DE22 3LS (GB)**
- **Hodgkinson, Elaine Christine**  
**Derby DE21 2JW (GB)**

(74) Representative: **Gunn, Michael Alan**  
**Rolls-Royce plc**  
**P.O. Box 31**  
**Derby DE24 8BJ (GB)**

(54) **A temperature indicating paint**

(57) An irreversible temperature indicating paint comprises 29wt% to 37wt% cobalt aluminium spinel and glass, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent. The solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether. A particular irreversible temperature indicating paint comprises 34.9wt% cobalt aluminium spinel and glass, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding sol-

vent. The irreversible temperature indicating paint has four or more colour changes in the temperature range 500°C to 900°C. The irreversible temperature indicating paint is used to determine the temperatures to which various parts of turbine blades, turbine vanes or other components are subjected in operation of the gas turbine engine.

## Description

[0001] The present invention relates to an irreversible temperature indicating paint.

[0002] Irreversible temperature indicating paint changes colour at one or more known temperatures. These colour changes of the temperature indicating paint indicate the temperature to which different parts of a component or components have been subjected. The final colour of the irreversible temperature indicating paint is dependent on both the temperature it is subjected to and the time period over which it is held at a raised temperature. The irreversible temperature indicating paint is applied to a component in a test situation and subsequently analysed to determine the temperatures to which different regions of the component reached during the test. Irreversible temperature indicating paints thus produce a temperature profile over the whole surface of a component rather than discrete points, if for example thermocouples are used.

[0003] Irreversible temperature indicating paints are applied to components, for example turbine blades, turbine vanes and combustors, of gas turbine engines and the gas turbine engine is run at the gas turbine engines normal operating conditions.

[0004] One known temperature indicating paint described in our UK patent GB1103059 comprises principally lead chromate, magnesium carbonate and silica.

[0005] Another known temperature indicating paint described in our UK patent GB2204874 comprises one or more of silver, gold, platinum, palladium, copper, nickel, chromium, titanium and silicon dispersed in 10 to 70wt% solvent and resin.

[0006] Currently used temperature indicating paint used in the temperature range 500°C to 900°C does not provide sufficient resolution of the temperature.

[0007] Accordingly the present invention seeks to provide a novel irreversible temperature indicating paint which has a plurality of colour changes in the temperature range 500°C to 900°C to provide improved temperature resolution.

[0008] Accordingly the present invention provides an irreversible temperature indicating paint comprising cobalt aluminium spinel, glass, a binder and a solvent.

[0009] Preferably the binder comprises acrylic resin and silicone resin.

[0010] Preferably the irreversible temperature indicating paint comprises 29wt% to 37wt% cobalt aluminium spinel and glass, 35wt% to 45wt% acrylic resin and 20 to 30wt% silicone resin excluding solvent.

[0011] Preferably the irreversible temperature indicating paint comprises 33wt% to 37wt% cobalt aluminium spinel and glass, 37.5wt% to 45wt% acrylic resin and 21 to 27.5wt% silicone resin excluding solvent.

[0012] Preferably the irreversible temperature indicating paint comprises 34wt% to 36wt% cobalt aluminium spinel and glass, 40wt% to 45wt% acrylic resin and 22 to 25wt% silicone resin excluding solvent.

[0013] Preferably the irreversible temperature indicating paint comprises 34.9wt% cobalt aluminium spinel, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent.

5 [0014] Preferably the solvent comprises a mixture of propylene glycol ethers. Preferably the solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether.

10 [0015] The present invention will be more fully described by way of example.

[0016] An irreversible temperature indicating paint according to the present invention has four or more colour changes in the temperature range 500°C to 900°C when run at maximum operating conditions of a gas turbine engine, or other engine, for 3 minutes.

15 [0017] The irreversible temperature indicating paint comprises cobalt aluminium spinel, glass, a binder and a solvent.

[0018] The irreversible temperature indicating paint broadly comprises 29wt% to 37wt% cobalt aluminium spinel and glass, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent. The solvent comprises a mixture of propylene glycol ethers, for example the solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether. The amount of solvent used is varied depending upon the particular method of applying the irreversible temperature indicating paint.

20 [0019] The irreversible temperature indicating paint more narrowly comprises 33wt% to 37wt% cobalt aluminium spinel and glass, 37.5wt% to 45wt% acrylic resin and 21wt% to 27.5wt% silicone resin excluding solvent.

25 [0020] Preferably the irreversible temperature indicating paint comprises 34wt% to 36wt% cobalt aluminium spinel and glass, 40wt% to 45wt% acrylic resin and 22wt% to 25wt% silicone resin excluding solvent.

30 [0021] A particular irreversible temperature indicating paint comprises 34.9wt% cobalt aluminium spinel ( $\text{CoAl}_2\text{O}_4$ ) and glass, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent. The cobalt aluminium spinel and glass is sold under the trade name 121603 Decorating Colour Blue by Degussa Metals Catalysts Cerdec AG of Geschäftsbereich Cerdec, P.O. Box 110403, D-60039 Frankfurt, Germany. The cobalt aluminium spinel may comprises two or more cobalt aluminium spinels comprising cobalt and aluminium which have a blue colour or blue green colour. Cobalt aluminium spinel comprises cobalt aluminate or cobalt aluminium oxide.

35 [0022] Decorating Colour Blue 121603 comprises glass and oxides having a CAS-No 65997-17-3, a cobalt aluminium spinel having a CAS-No 1345-16-0 and a cobalt aluminium spinel having a CAS-No 68187-11-1.

40 [0023] The irreversible temperature indicating paint has four or more colour change points in the temperature range 500°C to 900°C. The irreversible temperature indicating paint has improved temperature resolution in the temperature range 500°C to 900°C, particu-

larly in the temperature range 600°C to 800°C.

[0024] The irreversible temperature indicating paint is applied to turbine blades or turbine vanes or other components of gas turbine engines. The irreversible temperature indicating paint is used to determine the temperatures to which various parts of the turbine blade, turbine vane or other component are subjected in operation of the gas turbine engine. 5

[0025] The irreversible temperature indicating paint may be used on components in other engines or other machines or other apparatus to determine the temperature to which various parts of the component are subjected in operation. 10

15

### Claims

1. An irreversible temperature indicating paint comprising a binder and a solvent, **characterised in that** the irreversible temperature indicating paint comprises cobalt aluminium spinel and glass. 20
2. An irreversible temperature indicating paint as claimed in claim 1 wherein the binder comprises acrylic resin and silicone resin. 25
3. An irreversible temperature indicating paint as claimed in claim 1 or claim 2 comprising 29wt% to 37wt% cobalt aluminium spinel and glass, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent. 30
4. An irreversible temperature indicating paint as claimed in claim 3 comprising 33wt% to 37wt% cobalt aluminium spinel and glass, 37.5wt% to 45wt% acrylic resin and 21wt% to 27.5wt% silicone resin excluding solvent. 35
5. An irreversible temperature indicating paint as claimed in claim 4 comprising 34wt% to 36wt% cobalt aluminium and glass, 40wt% to 45wt% acrylic resin and 22wt% to 25wt% silicone resin excluding solvent. 40
6. An irreversible temperature indicating paint as claimed in claim 5 comprising 34.9wt% cobalt aluminium spinel and glass, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent. 45
7. An irreversible temperature indicating paint as claimed in any of claims 1 to 6 wherein the solvent comprises a mixture of propylene glycol ethers. 50
8. An irreversible temperature indicating paint as claimed in claim 7 wherein the solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether. 55

EP 1 291 395 A1



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 25 5948

DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim
A.D	GB 1 103 059 A (ROLLS ROYCE) 14 February 1968 (1968-02-14)	C09D5/26
A.D	GB 2 204 874 A (ROLLS ROYCE PLC) 23 November 1988 (1988-11-23)	

  

TECHNICAL FIELDS SEARCHED (Int.Cl. 7)
C09D G01K

  

The present search report has been drawn up for all claims.

THE HAGUE	Date of completion of the search	Searcher
CATEGORY OF CITED DOCUMENTS	9 December 2002	Miller, A

<ul style="list-style-type: none"> <li>X particularly relevant if taken alone</li> <li>Y particularly relevant if combined with another document of the same category</li> <li>A technological background</li> <li>I non-written disclosure</li> <li>W intermediate document</li> </ul>	<ul style="list-style-type: none"> <li>1 theory or principle underlying the invention</li> <li>2 earlier patent document, but published on or after the filing date</li> <li>3 document cited in the application</li> <li>4 document cited for other reasons</li> <li>5 member of the same patent family, corresponding document</li> </ul>
---	---